

C16 CLS Data Sheet

Imported	German or Swedish production. Slow grown imported timber is more durable and less susceptible to bow and twist.
C16 Strength Graded	Machine strength graded to a minimum of C16 in accordance with BS EN 14081.
PAR Eased Edge	Planed all round (PAR) with eased edges for ease of handling.
KD HT56/30	Kiln Dried in accordance with BS EN 14298 to maximise performance, stability and reduce weight. HT56/30 and ISPM15 Compliant.
100% PEFC Certified	Chain of custody ensures the timber was sourced responsibly and from sustainable sources.
Species	Predominantly European spruce (also known as Norway Spruce). Scientific name Picea Abies.
5 Side Plastic Wrapped	Untreated timber supplied with durable plastic wrapping on the top and 4 sides to protect the timber from the weather.
Webpage	www.jordeson.co.uk/CLS